

**Porcelain / Direct Screen Printing and Decals  
High Temperature Gold**



Colour	Product	Precious Metal Content	ASTM-resistant	microwave-resistant	Sanitary Ware	Notes*
yellow	SG 23/204	38%				firing range 1180-1230°C / 2155-2245°F
yellow	SG 21/204/209	38%				firing range 1180-1230°C / 2155-2245°F
yellow	PG 5818 S	38%				firing range 1200-1250°C / 2190-2280°F <b>new!</b>
yellow	SG 24/204	32%				firing range 1180-1230°C / 2155-2245°F
yellow	SG 41/UV	32%				UV-curing, firing range 1180-1230°C / 2155-2245°F
yellow	PG 5823	32%				firing range 1200-1250°C / 2190-2280°F <b>new!</b>
yellow	SG 26/204/209	26%				firing range 1180-1230°C / 2155-2245°F
yellow	PG 5822	26%				firing range 1200-1250°C / 2190-2280°F <b>new!</b>

\* High temperature precious metal pastes need to be stirred well before use