



Bright Precious Metal Preparations for Brush Application and for Spraying on Porcelain, Bone China, Earthenware and Tiles

1 General Information

Heraeus supplies bright precious metal preparations for porcelain, Bone China, earthenware and tiles with different precious metal contents. Depending on the precious metal content and the thickness of the precious metal application, a gold film of approx. 0.05 – 0.2 µm forms after firing.

2 Standard Firing Range

Substrate Type	Firing Range	
• Porcelain	780 - 880°C	(1436 - 1616°F)
• Bone China	750 - 880°C	(1380 - 1616°F)
• Vitreous China	750 - 850°C	(1380 - 1560°F)
• Earthenware	650 - 740°C	(1200 - 1365°F)
• Tiles	760 - 900°C	(1400 – 1650°F)

The firing result depends on the firing temperature, on the total firing time, the soak time and not least on the properties of the glaze. To achieve an optimized firing result, we therefore recommend the user to check under his own individual conditions.

3 Properties Of The Preparations

The major characteristics of a Heraeus precious metal preparation are determined by its production recipe. From each lot produced, we take a sample and check defined characteristics.

We check the physical properties (e. g. viscosity) and also the application properties (e.g. brushability) of our precious metal preparations for brush application against a predefined standard before firing. After the firing under defined conditions, we check the optical properties (gloss level and colour). Controlling each single production lot assures the highest product quality and lot-to-lot stability. The mayor characteristics of a Heraeus precious metal preparation are determined by its production recipe. From each produced lot we take a sample and check defined characteristics.



3.1 Processing

We deliver bright precious metal preparations for brush application ready to use. They can be applied without further thinning and distinguish themselves by their excellent application properties and outline. Storage

Since bright precious metal products contain precious metal organically bound, there is no sedimentation. Nevertheless, a minor sedimentation may occur in case of thin fluid preparations. Should there be any sedimentation, it must not be shaken and remains in the bottle.

Also bright precious metal products are subject to an ageing process. As a rule, the viscosity increases with the

The statements concerning our products correspond to our current knowledge and experience. It is the obligation of the purchaser to examine the usefulness of the products in its intended use in each individual case. In order to prevent production losses the user has to test the preparations in connection with every other material being involved in the production process and has to be satisfied that the intended result can be consistently produced.

W. C. Heraeus
Business Unit Precious Colours
Heraeusstraße 12-14
D-63450 Hanau
Phone: +49 (0) 6181 35 4420
Fax: +49 (0) 6181 35 9637
e-mail: preciouscolours@heraeus.com
internet: www.heraeus-preciouscolours.com

storage time. Therefore, we recommend to use the preparations within 12 months. They should be stored at room temperature (c. 20°C / 70°F).

Storage at approx. 7-14°C / 45-57°F reduces the increase of viscosity during the storage.

3.2 Consumption

The material consumption depends on the thickness of the applied precious metal layer. Under our conditions, the consumption is approx. 0.15 to 0.30 g /100 cm².

4 Properties Of Finished Decorations

The main properties of fired bright precious metal decorations comprise brilliance and precious metal tone, dishwasher resistance and resistance to mechanical and chemical attack.

These properties are influenced by a number of factors. The high quality of the preparation used is an absolute prerequisite for manufacturing high-quality decorations. The quality of a fired decoration, however, derives from the interplay of preparation, application, substrate surface and firing conditions. A variation in only one factor – for instance, the firing conditions, has an immediate influence that leads to altered properties of the fired decoration.

We have processed the bright precious metal preparations under defined conditions. Then we determined the properties of the finished decorations. The following data indicate achievable quality features for the finished decorations manufactured with bright precious metal preparations. They must, however, always be checked by the user under his own individual conditions.

4.1 Mechanical Resistance

The mechanical resistance of a precious metal decoration is influenced by the chemical composition of the used precious metal preparation and also by the substrate surface, the firing conditions and the layer thickness of the fired precious metal layer.

4.2 Dishwasher Durability

All details as to whether decorations are dishwasher durable are to be regarded as approximate values, as test results vary widely according to the type of dishwasher, washing programme, washing-up detergent, water quality and firing conditions.

Heraeus tests whether finished decorations are dishwasher durable, roughly following the test-washing programme of the Technical Standards Committee for Material Testing (Fachnormenausschuss Materialprüfung) in a Miele continuous dishwasher.

If a decoration withstands 500 washing cycles essentially without damage, we designate it as dishwasher durable. If it withstands 1000 washing cycles, we designate it as dishwasher resistant.

The user must test the required properties under his own conditions.

4.3 Silver Containing Precious Metal Preparations

To achieve lemonish, light yellow and yellow gold decorations, silver is added to the formulation of precious metal preparations. Silver containing precious metal decorations can change their appearance in the course of time, under certain unfavourable external circumstances. Especially the contact to cardboard boxes, high humidity and high temperature support the reaction of silver to silver sulphide. Therefore, the user must individually check the suitability of a silver containing preparation.

Products with a higher silver content we labeled as "silver containing". We recommend to hermetically package items decorated with precious metal preparation we describe as "silver containing", and to prevent direct contact with cardboard boxes. To exclude any risk, we recommend using yellow red gold preparations.

The statements concerning our products correspond to our current knowledge and experience. It is the obligation of the purchaser to examine the usefulness of the products in its intended use in each individual case. In order to prevent production losses the user has to test the preparations in connection with every other material being involved in the production process and has to be satisfied that the intended result can be consistently produced.

5 Application Recommendations

5.1 Conditions Required For Good Results

- Work in a well-ventilated room. Good printing conditions occur at a room temperature of 20 to 25°C.
- Make sure that the surface of the object to be decorated is clean and dry. Dust, fingerprints and water condensation can affect the decoration while firing.
- Take care that the object to be decorated is not taken from a cold store into a warm shop. A fine condensation film may occur, which is not visible for the naked eye. Result: Firing disturbance (pinholes) in the fired precious metal decoration! Allow enough time for the material to adjust to the decoration room temperature.

5.2 Application Information

- Do not shake the bright precious metal preparations prior to use.
- Draw from the bottle only as much as you can consume within 15 or 30 minutes and close the bottle. Consider that the solvent continuously evaporates in air and therefore the viscosity slowly increases.
- Apply the preparation in a moderate layer thickness onto the object to be decorated. A too thin layer influences the mechanical, chemical and optical properties of the fired decoration. In extreme cases, it can lead to a reddish colour of the surface without any gold character. A too thick layer may lead to cracking, blistering, or to a matt surface.
- In case the preparation is used for spraying, thinning with about 30% thinner V 35, V 16 or V 18 is required.

5.3 Firing

- During the heating up phase, first of all the organic components of the preparation burn off. This process is completed at approx. 400°C (750°F). The gold film is formed. A constant, slow temperature increase, enough oxygen and sufficient ventilation are decisive for the quality of the fired precious metal decoration.
- The firing profile considerably influences the mechanical and chemical properties of the fired decoration.
- The rate of cooling has no major influence on the quality of the gold decoration, unlike the firing temperature and soak time. However, the firing process should not be stopped too abruptly after the soak time. In case the decorated article cools down too quickly, there is a danger of cracks in the glaze.

6 Frequent Faults, Their Causes And Ways Of Avoiding Them

Fault	Possible Cause	Remedy
blurred contours, running precious metal	too much thinning of the product	leave the bottle open for a while, so that some of the solvent can evaporate
	the thinner was too fat or drying too slowly	leave the bottle open for a while, so that some of the solvent can evaporate
	too much organic fumes in the furnace	reduce the number of objects in the furnace
preparation shows bad application	viscosity is too high after long application or long storage	thinning of the product with V 35, V 16 or V 18
spots, firing disturbance	contamination as dust, fingerprints or water condensation	Carefully clean the object before decorating
	problems in the kiln such as: <ul style="list-style-type: none"> • reduced atmosphere in kiln • insufficient ventilation • heat increase is too fast during critical phase between 200-400°C (390-750°F) • too many objects in the kiln 	<ul style="list-style-type: none"> • increase air addition • improve ventilation • reduce the heating speed • reduce the number of the objects in the kiln
Precious metal chips offs during firing	contamination of the surface causes chip off	clean the substrate before decorating
	the layer of the product it too thick	reduce layer of the product
low mechanical resistance of the precious metal decoration	firing temperature is too low	increase firing temperature
	layer of the product is too thin	increase layer thickness
fine pinholes	pinholes can be released by moisture on the surface of the decorated object. Taking objects from a cool store into a warm shop leads to invisible condensation on the surface.	allow enough time for the ware to reach shop temperature, so that the condensation has time to evaporate.

The statements concerning our products correspond to our current knowledge and experience. It is the obligation of the purchaser to examine the usefulness of the products in its intended use in each individual case. In order to prevent production losses the user has to test the preparations in connection with every other material being involved in the production process and has to be satisfied that the intended result can be consistently produced.

W. C. Heraeus

Business Unit Precious Colours
Heraeusstraße 12-14
D-63450 Hanau
Phone: +49 (0) 6181 35 4420
Fax: +49 (0) 6181 35 9637
e-mail: preciouscolours@heraeus.com
internet: www.heraeus-preciouscolours.com

7 Bright Gold Preparations For Brush Application And For Spraying On Porcelain

Colour	Product	Precious Metal Content	ASTM-resistant	microwave-resistant	Sanitary Ware	Notes	
light yellow	GG 347	8+10+12%				wide firing range, suitable for etch imitation	
light yellow	GG 346	8+10+12%				wide firing range, suitable for etch imitation	
light yellow	GZ 215	10+12%				lemon yellow firing result, suitable for etch imitation	<i>new!</i>
yellow	GG 522	12%				wide firing range: 760-900°C / 1400-1650°F	<i>new!</i>
yellow	GG 95/3	10+12%	●	●		excellent chemical and mechanical resistance	
yellow	GG S3D	10+12%				-	
yellow	GG 1539	10+11%				suitable for etch imitation	
yellow	LU 32	5,4%				gold lustre	<i>new!</i>
reddish yellow	GG NZ	8+10+11+12%				-	
reddish yellow	GG 500	8+10+12%				excellent chemical resistance	<i>new!</i>
reddish yellow	GG 501	7-12%				excellent chemical resistance	<i>new!</i>
reddish yellow	GG 550	10+11%				excellent chemical resistance, especially suitable for application on large areas	<i>new!</i>
reddish yellow	GG 577	10%				excellent chemical resistance	<i>new!</i>
reddish yellow	GG 532	10%				suitable for application on large areas	<i>new!</i>
reddish yellow	GG 573	10%		●		microwave-resistant, very resistant to abrasion	<i>new!</i>
reddish yellow	GG 1518/MW	5+9%		●		microwave-resistant, very resistant to abrasion	
copper	ST 26	5%				copper lustre	

The statements concerning our products correspond to our current knowledge and experience. It is the obligation of the purchaser to examine the usefulness of the products in its intended use in each individual case. In order to prevent production losses the user has to test the preparations in connection with every other material being involved in the production process and has to be satisfied that the intended result can be consistently produced.

8 Bright Gold Preparations For Brush Application And For Spraying On Bone China

Colour	Product	Precious Metal Content	ASTM-resistant	microwave-resistant	Sanitary Ware	Notes
yellow	GG E FL 8	15%				-
reddish yellow	GG 1300	10%				wide firing range
reddish yellow	GG 575	10+12%				-
reddish yellow	GG 1518/MW	5+9%		●		excellent resistance to abrasion

new!

9 Bright Gold Preparations For Brush Application And For Spraying On Tiles

Colour	Product	Notes
yellow	GG 3015 D	-
yellow	GG 1401	excellent brushability, excellent mechanical and chemical resistance
yellow	GG 1402	excellent brushability, excellent mechanical and chemical resistance
reddish yellow	GG NZ	well-tried standard preparation
reddish yellow	GG 3014 D	well-tried standard preparation, excellent brushability, excellent mechanical and chemical resistance
reddish yellow	GG 301	-
reddish yellow	GG 700	-
reddish yellow	GG 234 55	-

new!

new!

new!

The statements concerning our products correspond to our current knowledge and experience. It is the obligation of the purchaser to examine the usefulness of the products in its intended use in each individual case. In order to prevent production losses the user has to test the preparations in connection with every other material being involved in the production process and has to be satisfied that the intended result can be consistently produced.

10 Bright Platinum Preparations For Brush Application And For Spraying On Porcelain

Colour	Product	Precious Metal Content	ASTM-resistant	microwave-resistant	Sanitary Ware	Notes	
white platinum	GP P 12/1	12%				suitable for etch imitation	
white platinum	GP 500	10%				-	<i>new!</i>
white platinum	GP 510 B	9%				-	<i>new!</i>
white platinum	GP IA/S	8%				-	
white platinum	GP 3510					wide firing range	
white platinum	GP 574			●		-	<i>new!</i>
white platinum	GP 318 F					-	<i>new!</i>
white platinum	GP 350					-	<i>new!</i>
white platinum	TGP0073A					-	<i>new!</i>
platinum	GP 3309/1	13%	●		●	-	
platinum	GP 1404/5	9%				suitable for etch imitation	
platinum	GP 1404/6	8%				suitable for etch imitation	
platinum (rosé)	N 605	4%				platinum lustre	
platinum	N 608	4%				platinum lustre	
platinum	N 607	3%				platinum lustre	

The statements concerning our products correspond to our current knowledge and experience. It is the obligation of the purchaser to examine the usefulness of the products in its intended use in each individual case. In order to prevent production losses the user has to test the preparations in connection with every other material being involved in the production process and has to be satisfied that the intended result can be consistently produced.

11 Bright Platinum Preparations For Brush Application And For Spraying On Bone China

Colour	Product	Precious Metal Content	ASTM-resistant	microwave-resistant	Sanitary Ware	Notes	
white gold	GP 558	9%				-	<i>new!</i>
white gold	GP 574			●		excellent resistance to abrasion	<i>new!</i>
white platinum	GP 3309/1	13%				-	
white platinum	GP 3300	9%	●			-	
platinum	GP 3301	7%				-	

12 Bright Platinum Preparations For Brush Application And For Spraying On Tiles

Colour	Product	Notes	
white	GP 3510	-	
white	GP 1404/6	-	
white platinum	TGP0073A	-	<i>new!</i>
white platinum	GP 350	-	<i>new!</i>
white platinum	GP 318 F	-	<i>new!</i>
white platinum	GP 574	-	<i>new!</i>

The statements concerning our products correspond to our current knowledge and experience. It is the obligation of the purchaser to examine the usefulness of the products in its intended use in each individual case. In order to prevent production losses the user has to test the preparations in connection with every other material being involved in the production process and has to be satisfied that the intended result can be consistently produced.